



(19)

(11) Publication number: **04063301 A**

Generated Document.

**PATENT ABSTRACTS OF JAPAN**

(21) Application number: 02174562

(51) Intl. Cl.: G02B 1/04 C08F 12/30 C08F 20/08

(22) Application date: 03.07.90

(30) Priority:		(71) Applicant: NIPPON OIL & FATS CO LTD
(43) Date of application publication:	28.02.92	(72) Inventor: MIYAZAKI TAKESHI MURATA TAKASHIGE
(84) Designated contracting states:		(74) Representative:

**(54) OPTICAL RESIN****(57) Abstract:**

**PURPOSE:** To provide the optical resin which has excellent characteristics, such as transparency, refractive index, chromatic aberration, optical distortion, has slight smells and has a good handling characteristic at the time of curing by polymerizing a raw material monomer contg. a specific org. sulfur compd.

**CONSTITUTION:** The optical resin is formed by polymerizing the raw material monomer contg. the org. sulfur compd. expressed by formula I [where A denotes formula II. (In the formula, R3 denotes a hydrogen atom or methyl group); R1 and R2 denote 1 to 6C alkyl groups which are the same or different groups; X denotes a chlorine atom, bromine atom or iodine atom. Further, l, m and n respectively denote 0 to 2.]. This org. sulfur compd. is easily prepd. by the reaction of, for example, 1mol equiv. 2-mercaptobenzothiazole and 1mol

equil. 2-hydroxy-3-chloropropyl methacrylate, etc. The compounding ratio of the above-mentioned org. sulfur compd. with the entire part of the raw material monomer is not particularly limited and is preferably in a 1 to 100wt.% range, more particularly preferably in a 50 to 100wt.% range.

COPYRIGHT: (C)1992, JPO&Japio

